



COMPOUND DATA SHEET

Parker O-Ring & Engineered Seals Division, North America

MATERIAL REPORT

Report Number: 87005

Test Date: 5/30/2012

Title: Evaluation of Parker Compound S0604-70

Elastomer Type: Silicone (VMQ, PVMQ)

Purpose: Testing to A-A-59588A

Specification: A-A-59588A

Color: Rust

Recommended Temperature Range: -65°F to 450°F

Recommended For: Animal, Vegetable oil, grease, high molecular weight chlorinated aromatic hydrocarbons (including flame resistant insulators, and coolant for transformers), moderate weather resistance, diluted salt solutions, and ozone.

Not Recommended For: Superheated water/steam over 250°F, acids and alkalis, low molecular weight chlorinated hydrocarbons, hydrocarbon based fuels, aromatic hydrocarbons (benzene, toluene), and low molecular weight silicone oils.

Additional Approvals: AMS 3304
AMS 3357
MIL-G-21569 Class 2
A-A-59588 Class 2a, 2b, grade 70
UL Approval

*"Purchaser use only. Reproduce only in full. Data pertains to items referenced only.
The recording of false, fictitious, or fraudulent statements or entries in the report may be punishable
as a felony under federal law."*

<u>Original Physical Properties</u>	<u>Test Method</u>	<u>Spec Limits</u>	<u>Results</u>
Hardness, Shore A, pts	ASTM D2240	70 ± 5	70
Tensile Strength, psi, Min	ASTM D412	650	1214
Ultimate Elongation, % Min	ASTM D412	80	190
Specific Gravity	ASTM D297	1.43 ± 0.03	1.41
<u>Compression Set</u>			
<u>70 hrs @ 150°C (302°F)</u>			
Percent of Original Deflect, Max	ASTM D395 Method B	25	16
<u>Dry Heat Resistance</u>			
<u>70 hrs @ 225°C (437°F)</u>			
Hardness Change, pts.	ASTM D573	±10	+3
Tensile Strength Change, %		-25	-10
Elongation Change, %		-40	-16
<u>Fluid Immersion</u>			
<u>Distilled Water, 70 hrs @ 100°C (212°F)</u>			
Volume Change	ASTM D471	+5	-1
<u>Low Temp Brittleness</u>			
Nonbrittle after 3 min @ -62.2°C (-80°F)	ASTM D2137	Pass	Pass